

Powercrete® R-65/F1 Pipeline Rehabilitation and Girth Weld Coating Fast Cure Liquid Epoxy Coating



Product Description

Powercrete R-65/F1 is a 100% solids liquid epoxy coating with a fast cure time for efficient, user-friendly application and rapid backfill. In addition to ease of application, R65/F1 provides excellent long term corrosion protection for bare steel or FBE coated pipe. This high-build, two-component epoxy can easily achieve a dry film thickness (DFT) of up to 40+ mils (1 mm) in a single application.

Powercrete R-65/F1 can be applied using plural component spray equipment or by hand brush, roller or trowel. Powercrete R-65/F1's unique combination of handling and performance characteristics make it the ideal coating for pipes, girth welds and/or the repair & rehabilitation of existing pipelines.

Product Features & Benefits

- **100% Solids Epoxy: no V.O.C.s / no Isocyanates**
Safe to use.
- **Super Fast Cure Time**
Speeds up production time and saves costs.
- **High Build: 1 mm (40 mils) in a Single Pass**
Saves time and costs.
- **Compatible with Bare Steel or FBE Coated Pipe**
Flexible use & reduces inventory.
- **2:1 Part A:B Mix Ratio by Volume**
Sprayable with conventional plural component equipment.
- **High Adhesion and Abrasion Resistance**
Superior performance for superior asset protection.
- **High Wet Out for Ultra High Surface Anchorage**
Longer life, better performance.
- **Same Formula for Hand or Spray Application**
Flexible and reduced inventory. Saves money.
- **Excellent Cathodic Disbondment at maximum operating temperature.**
Broad range of applications.

Typical Applications



- Pipeline Coating (Girth Welds, Pipe Bends, Fittings, Valves, Odd Shapes), Repair & Rehabilitation

Physical Properties

Property	Condition	Test Method	Typical Value	
			US Imperial	Metric
Hardness	(Shore D)	ASTM D-2240	85	85
Thin Film Water Absorption		ASTM D-570	0.22 %	0.22 %
Dielectric Strength	(Oil)	ASTM D-149	617 volts/mil	25 kV/mm
Chemical Resistance		ASTM G-20	Excellent	Excellent
<i>Adhesion to</i>				
FBE		ASTM D-4541	> 3,000 psi	21 MPa
Bare Steel		ASTM D-4541	> 3,400 psi	23 MPa
Impact Resistance		ASTM G-14	118 inch-lb/27mils	13 Joules/27mils
Flexibility	(Degrees per pipe diameter)	NACE RP-0394	< 0.45 °	< 0.45 °
Abrasion Resistance	(CS-17 wheel, wear cycles)	ASTM D-4060	986 cycles/mil	39 cycles/micron
Cathodic Disbondment	(30 days at 60°)	ASTM G-95	< 0.4 inch	< 10 mm
Hot Water Immersion	(24 hours immersion at 60°C)	CSA Z245-20-06	100% coating cohesion >3,000 psi	100% coating cohesion >21 MPa
Holiday Detection	Holiday free	ISO : 21809-3 & CSA Z245.20	125 Volts per mil	5 Volts per micron
		ASTM G 62 Method B	84 Volts per mil	3.3 Volts per micron

Product Selection Guide

Maximum Operating Temperature:	65°C (149°F)	Color:	Green
Compatible Line Coatings:	FBE	Typical Single Coat Thickness:	
Mixing Ratio:	2:1 Part A to B	Manually Applied	40 mils (1.0 mm)
		Spray Applied	40 mils (1.0 mm)
By Weight	100:36 Part A to B	Recoat Interval (Spray):	
Recommended Surface Profile	2.5 - 4.0 mils 63.5 - 101.6 microns	@ 25°C (77°F)	10 - 17 minutes
		@ 43°C (110°F)	3 - 7 minutes
Surface Preparation:	SA 2 1/2 SSPC-10 - Near-White SSPC-SP5 - White	Theoretical Coverage:	13.5 Sq. Ft./liter @30 mils
		Clean Up:	Acetone, MEK, Toluene

Hand Apply	Coverage Rates	Spray Apply	Waste Factor													
	Theoretical Coverage Rates 425 mil-sq. ft./litre 1605 mil-sq. ft./US gallon 1.0 mm-m ² /litre															
	Recommended Tip Sizes															
	<table border="1"> <thead> <tr> <th>Tip Size</th> <th>Pipe Size (DN)</th> <th>Flow Rates (approx.)</th> </tr> </thead> <tbody> <tr> <td>331</td> <td>to 12" (DN300)</td> <td>19tip = 1.1L / min.</td> </tr> <tr> <td>419/431</td> <td>12"-16" (DN300-400)</td> <td>31tip = 2.8L / min.</td> </tr> <tr> <td>519/531</td> <td>16"-24" (DN400-600)</td> <td></td> </tr> <tr> <td>619/631</td> <td>24"-48" (DN600-1200)</td> <td></td> </tr> </tbody> </table>	Tip Size		Pipe Size (DN)	Flow Rates (approx.)	331	to 12" (DN300)	19tip = 1.1L / min.	419/431	12"-16" (DN300-400)	31tip = 2.8L / min.	519/531	16"-24" (DN400-600)		619/631	24"-48" (DN600-1200)
Tip Size	Pipe Size (DN)	Flow Rates (approx.)														
331	to 12" (DN300)	19tip = 1.1L / min.														
419/431	12"-16" (DN300-400)	31tip = 2.8L / min.														
519/531	16"-24" (DN400-600)															
619/631	24"-48" (DN600-1200)															
Waste Factor (approx.)																
			<table border="1"> <thead> <tr> <th>Waste Factor</th> <th>Kit Application</th> </tr> </thead> <tbody> <tr> <td>10%</td> <td>20" + pipe OD</td> </tr> <tr> <td>15%</td> <td>14"-18" pipe OD</td> </tr> <tr> <td>25%</td> <td>2"-12" pipe OD</td> </tr> </tbody> </table>	Waste Factor	Kit Application	10%	20" + pipe OD	15%	14"-18" pipe OD	25%	2"-12" pipe OD					
Waste Factor	Kit Application															
10%	20" + pipe OD															
15%	14"-18" pipe OD															
25%	2"-12" pipe OD															

Temperature Considerations

If the surface to be coated is below 10°C (50°F), preheating of the substrate is recommended. Preheat temperatures should not exceed 80° C (176° F) prior to application.

Note: The application should only be done when temperature of the steel is at least 3°C (5°F) higher than the dew point, as recommended by NACE.

Storage and Handling

For optimum performance, store Powercrete R-65/F1 epoxy product in a dry well ventilated area. Maintain products in original packaging and sealed until just before use. Avoid exposure to direct sunlight, rain, snow, dust, and other adverse environmental conditions or contaminants.

Always consult Material Safety Data Sheet prior to handling Powercrete R-65/F1.

Note: Avoid prolonged storage at temperatures above 40° C (104° F) or below 5° C (40° F)

Cure Times @ 25°C (77°F)

Pot Life: 0.5 L / 2 Lb kit	9 minutes
Spray Application	
Gel T 40 mils	12 minutes
Dry Time: 40 mils	37 minutes
65 Shore "D" Reading: 40 mils	60 minutes
75 Shore "D" Reading: 40 mils	75 minutes

Shelf life (stored in specified conditions):	Part A - 2 years
	Part B - 1 years

Ordering Information

1. Drums

260714-000 **Part-A Drum:** PC R65F1-A-156L-41GL-299KG-660Lb
 260902-000 **Part-B Drum:** PC R65F1-B-156L-41GL-215KG-475Lb

2. Pails

351587-000 **Part-A Pail:** PC R65-F1-A-13L-3.5GL-55LB-25KG
 544803-000 **Part-B Pail:** PC R65-F1-B-13L-3.5GL-40LB-18KG

3. Kits

1247-000 0.5 L **Kit:** PCR65F1-0.5L-0.9KG-2LB-KIT
 124017-000 1 L **Kit:** PCR65F1-1L-1.7KG-4LB-KIT
 690692-000 2.5 L **Kit:** PCR65F1-2.5L-4.3KG-10LB-KIT

4. Self-Mixing Cartridges

Repair Cartridge (50 ML, 2:1 mix-ratio) and Spray Cartridge (400 ML, 1:1 mix-ratio) also available.

5. Accessories Kit (optional)

(Accessories Kit contains Latex Gloves, trowels, mixing paddle for electrical drill, hand stirrer, wet film thickness gauge, disposable face masks)



Product Support and Additional Information

For additional information on delivery, application, training, appropriate equipment, sales and customer service, please visit www.berrycpg.com, call or email one of the worldwide locations listed below.



The leading global partner in protecting the integrity of critical infrastructure.

Berry Plastics warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Berry Plastics written instructions. Since many installation factors are beyond the control of Berry Plastics, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastics liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date.

Local Distributor / Representative:

For contact details of local Distributors / Representatives
 Please visit www.berrycpg.com.

Headquarters
 Franklin, MA, USA
 Tel: +1 508 918 1714
 US Toll Free: +1 800 248 0149
 Fax: +1 508 918 1910
 CPG@berrypastics.com

Houston, TX, USA
 Tel: +1 713 676 0085
 US Toll Free: +1 888 676 7202
 Fax: +1 713 676 0086
 CPGH@berrypastics.com

Tijuana, Mexico
 Tel USA +1 858 633 9797
 Fax US: +1 858 633 9740
 Tel Mexico: +52 664 647 4397
 Fax Mexico: +52 664 607 9105
 CPGTJ@berrypastics.com

Westerlo, Belgium
 Tel. +32 14 722500
 Fax +32 14 722570
 CPGE@berrypastics.com

Baroda, India
 Tel: +91 2667 264721
 Fax: +91 2667 264724
 CPGIN@berrypastics.com